## GEMMOLOGICAL INSTITUTE OF INDIA®

(A Project of The Gem & Jewellery Export Promotion Council)

Co-sponsored by:

224625

Bharat Diamond Bourse • Diamond Exporters' Association Limited • Gem & Jewellery Exporters' Association • Mumbai Diamond Merchants' Association GEM TESTING LABORATORY • DIAMOND GRADING LABORATORY • RECOGNIZED AS SIRO LAB BY THE DEPARTMENT OF SCIENCE AND TECHNOLOGY, GOVERNMENT OF INDIA

GEMSTONE REPORT

Date: 03-Apr-2023



GEM-22102021-040

On receipt of your letter, we undertook testing and identification of the Gemstone / Mineral entrusted to us/our representative at our Laboratory. The results obtained are given below :-

Weight in Cts : 12.920 Cts

Mounted or Unmounted : UNMOUNTED

Colour : GREEN

Type of cut : OCTAGON STEP CUT

Dimensions : 1) 6.88 cts. (12.17 x 12.15 x 6.53 mm.) Approx

2) 6.04 cts. (12.23 x 12.21 x 6.02 mm.) Approx

Other Tests : FTIR indicates enhancement by oil

Remarks : Emeralds are generally enhanced by oil



Silvia Sequeira, FGA

Mahesh Gaonkar, FGA,MSc

(Gemmologist) (Gemmologist)

IDENTIFICATION

\* \* \* EMERALDS-NATURAL \* \* \*

(Indication of Minor Enhancement with Oil Observed)





